

(12) UK Patent Application (19) GB (11) 2 399 868 (13) A

(43) Date of A Publication 29.09.2004

(21) Application No: 0402248.9
(22) Date of Filing: 27.03.2003
Date Lodged: 02.02.2004
(62) Divided from Application No
0307120.6 under Section 15(4) of the Patents Act 1977

(71) Applicant(s):
Minebea Co Ltd
(Incorporated in Japan)
4108-73 Oaza Miyota,
Miyota-machi Kitasaku-gun,
Nango 389-0293, Japan

(continued on next page)

(51) INT CL⁷:
F16C 33/04

(52) UK CL (Edition W):
F2A AD44 A121 A150

(56) Documents Cited:
JP 610115625 A

(58) Field of Search:
UK CL (Edition W) F2A
INT CL⁷ F16C
Other: WPI, EPODOC, PAJ

(54) Abstract Title: **A lined and flanged bush**

(57) A lined and flanged bush comprises a spigot having a flange 3 which provides a flange surface 6 surrounding the spigot; and a liner 5 having an aperture through which the spigot is located, wherein there is an adhesive bond between the flange surface 6 and the liner 5 and a mechanical bond between an outer edge of the liner 5 and the edge of the flange 3. The liner 5 preferably includes a metal mesh and maybe self-lubricating. The mechanical bond is preferably provided by a stamping process which cuts firstly through the liner 5 and then through the material of the flange 3 to provide an element of compression at the very edge of the flange surface 6.









FIG. 2

GB 2399868 A continuation

(72) Inventor(s):
David Shore
Chris Bennett

(74) Agent and/or Address for Service:
Forrester Ketley & Co
Forrester House, 52 Bounds Green Road,
LONDON, N11 2EY, United Kingdom








FIG. 6

PATENTS ACT 1977

Agents Ref: Q17504GB-LH/mf

5 A LINED AND FLANGED BUSH

This invention relates to a bush and more particularly to a lined and flanged bush.

10 Blow-down panel bushes are used in aerospace applications and comprise a flanged bush to which a ring of self-lubricating liner is bonded. The component is manufactured and machined on a piece-by-piece basis and is small, standing approximately 4mm high with a rounded rectangular base being approximately 20mm long and 16mm wide.

15

Once the flanged bush has been machined to provide a spigot with a central bore upstanding from the surrounding flange surface, the ring of self-lubricating liner is cut to size and bonded to the flange surface. Great care must be taken to ensure that a constant and consistent pressure is applied to the liner
20 to effect a good adhesive bond between the liner and the flange surface. After bonding is complete, the outer edge of the ring of self-lubricating liner must be trimmed to ensure that no part of the liner protrudes beyond the edge of the flange surface and to ensure that there is no fretting of the liner edge. It is imperative that the liner edge is fully bonded right up to the edge of the flange
25 surface.

With such small pieces of manufacture, it is difficult to maintain a good quality finished product. The manufacturing process is labour-intensive, involves many steps and is also expensive.

It is an object of the present invention to ameliorate the above-mentioned disadvantages.

5 Accordingly, one aspect of the present invention provides a flanged bush comprising: a spigot having a flange which provides a flange surface surrounding the spigot; and a liner having an aperture through which the spigot is located, wherein there is an adhesive bond between the flange surface and the
10 the flange.

In order that the present invention may be more readily understood, embodiments thereof will now be described, by way of example, with reference to the accompanying drawings, in which:

15

Figure 1 is plan view of a flanged bush embodying the present invention;

Figure 2 is a cross-section through the bush of Figure 1 taken along line A-A;

20 Figure 3 is a plan view of a billet of material machined to provide an array of upstanding spigots;

Figure 4 is a plan view of a self-lubricating liner for use with the billet of Figure 3;

25

Figure 5 is a plan view of the liner of Figure 4 registered with the billet of Figure 3 and showing the intended punch lines for individual bushes; and

Figure 6 is a detail of the bush of Figure 2.

Referring to Figures 1 and 2, a flanged bush 1 embodying the present invention is configured, in this case, as a blow-down panel bush and comprises a spigot 2
5 surrounded by a flange 3. The spigot 2 and flange 3 are substantially rectangular in plan view, the corners of the rectangles being rounded as shown in Figure 1. A central bore 4 runs through the spigot 2.

A ring of self-lubricating liner 5 such as a PTFE enriched woven metal or
10 plastic mesh reinforced by resin sits on the flange surface 6 surrounding the spigot 2. The spigot 2 passes through an aperture 7 in the ring of liner material. There is a clearance gap 8 between the spigot 2 and the liner 5. The liner 5 is adhesively bonded to the flange surface 6.

15 A method for manufacturing a bush as shown in Figures 1 and 2 comprises the following steps. Firstly, a bar of steel is cut to provide a billet 10 which will provide a blank from which the method embodying the present invention will provide, in this example, ten flanged bushes 1.

20 Referring to Figure 3, one surface of the billet 10 is machined to leave ten upstanding spigots 2 in a regular array across the surface of the billet 10. A central bore 4 is machined through each of the spigots 2. Further, a pair of registration holes 11 are drilled through the billet 10. The registration holes 11 are provided on different radial axes so as not to be symmetrical with one
25 another about any axis of the billet 10.

Referring now to Figure 4, a sheet of self-lubricating liner 5 is provided into which are cut ten apertures 7 dimensioned to surround, with a clearance gap 8,

each of the spigots 2. The apertures 7 in the liner are arranged in the liner sheet so as to register with the spigots 2 on the billet 10.

5 The liner 5 is also provided with two registration holes 12, which are intended to be aligned with the registration holes 11 on the billet 10 when the spigots 2 pass through their respective apertures 7 in the liner 5.

10 An adhesive is applied to the liner 5 and the billet surface or the liner 5 may comprise a self-adhesive surface on the surface of the liner 5 facing the surface of the billet 10.

15 Registration pins 13 are located in registration holes 11 and the liner 5 is laid over the billet 10 lining up the registration holes 12 with the registration pins 13 until the liner sits on the surface of the billet 10 with the spigots 2 protruding through the apertures 7 in the liner 5.

20 The liner 5 and the billet 10 are pressed together and a consistent and constant pressure is applied over the large surface area of the liner 5 pushing the liner 5 and billet 10 together to ensure a good adhesive bond between the liner 5 and the billet 10 over the complete surface area of the billet. It is much easier to provide a consistent pressure over the relatively large surface area of a billet 10 containing an array of many spigots 2 than over a ring of liner on a single flanged bush 1.

25 Referring now to Figure 5, the billet 10 and liner 5 are placed in a stamping machine which is arranged to punch out simultaneously ten flanged bushes 1 from the billet 10. In Figure 5, there is a dashed line 14 drawn around each of the spigots 2. This line comprises the punch line 14 or the line of cut which the

stamping machine will create, effectively being the outline 14 of each of the flanged bushes 1.

5 The remaining surface of the billet 10 is punched away from the outlines 14 of the flanged bushes 1 leaving the flanged bushes 1 remaining. The stamping process cuts firstly through the liner 5 and then the material of what will comprise the flange 3 so that there is an element of compression of the liner 5 at the very edge of the flange surface and, indeed, the shearing action of the punching or stamping step creates a mechanical bond between the liner 5 and
10 the flange 3 at the punch line 14, thus ensuring that the liner 5 is fully bonded around the edge of the flange to the flange.

The stamping operation means that the previous manufacturing steps, used to produce a conventional panel bush, of trimming the liner 5 around the edge of
15 the flange and removing the excess glue from between the liner and the edge of the flange are no longer required. The shearing action of the stamping or punching step means that the liner is very neatly finished with respect to the edge of the flange 3 and, as shown in Figure 6, particularly when a metal mesh is used in the liner 5, there is an element of a mechanical bond 15 between the
20 liner 4 and the flange 3 at the point of contact between the liner 5 and the flange 3 around the edge of the flange 3.

Another advantage of the use of the stamping technique where the liner has been pre-applied to the billet is the fact that the pressure can be applied to the
25 liner more consistently over the large surface area of the billet 10 containing many bushes 1 as opposed to just on a single bush 1.

There is an additional advantage in that manufacturing the bushes from a reasonably sized, if not large, billet, is far preferable from a handling point of view to manufacture the bushes on an individual piece-by-piece basis.

- 5 In the present specification "comprises" means "includes or consists of" and "comprising" means "including or consisting of".

CLAIMS:

1. A flanged bush comprising: a spigot having a flange which provides a flange surface surrounding the spigot; and a liner having an aperture through
5 which the spigot is located, wherein there is an adhesive bond between the flange surface and the liner and a mechanical bond between an outer edge of the liner and the edge of the flange.
2. A flanged bush according to Claim 1, wherein the liner includes a metal
10 mesh.
3. A flanged bush according to Claim 1 or 2, wherein the liner is a self-lubricating liner.
- 15 4. A flanged bush according to any preceding claim, wherein the mechanical bond is provided by a stamping process which cuts firstly through the liner and then the material of what will comprise the flange to provide an element of compression of the liner at the very edge of the flange surface and create the mechanical bond between the liner and the flange thus ensuring that
20 the liner is fully bonded around the edge of the flange to the flange.
5. A flanged bush substantially as hereinbefore described with reference to and as shown in the accompanying drawings.